

TECHNICAL DATA SHEET

CA PLUS No Odor / No Bloom: 5cps, 100cps, 500cps, 1000cps Cyanoacrylates.

Product Description: This advanced performance series of CA PLUS Cyanoacrylates are a family of products that have been designed and manufactured to meet the demands of today's product assembly requirements while at the same time eliminating odors and blooming. Standard Cyanoacrylates are generally eye and nose irritants. CA PLUS No Odor / No Bloom family of cyanoacrylates eliminates odors and fumes that cause irritation and the whitening effect around the bond line. (Sometimes called blooming.)

<u>Physical Properties:</u>	5	100	500	1000
(Uncured Properties)				
Base Compound	-----Modified Cyanoacrylate-----			
Appearance	-----Colorless, transparent liquid-----			
Viscosity @ 20°C	5	100	500	1000
Flash Point (TCC)	----->200°F-----			
Specific Gravity	-----1.10-----			
Shelf Life	-----One year-----			
Soluble in	-----Nitromethane-----			

<u>Cured Properties:</u>				
Softening Range	-----264°F to 273°F-----			
Melting Point	-----327°F to 345°F-----			
Hardness (Shore A)	-----85-----			
Weatherability	-----No change observed after 200 hours-----			
Solubility	-----Nitromethane-----			
Fixture Time (Sec)	<10	<10	<10	<25
Full Cure	-----24 Hours-----			
Tensile Shear	-----1900 – 2700 psi-----			
Impact Resistance	-----4 – 9 ft. lbs (ASTM D950)-----			
Gap fill (Inches)	.002	.006	.007	.008
Temp. Range	----- -65°F to +180°F-----			

Preparation:

For best results and optimum adhesive performance, surfaces should be clean and free from contaminants. Contaminants can be removed by using suitable solvents. When using a cleaning solvent, first check for material compatibility particularly in the case of plastics. An easy method for removing contaminants is by using a clean cloth and wiping the surface with acetone or alcohol.

Application:

The advanced performance series of CA PLUS No Odor / No Bloom Cyanoacrylates should be applied in small amounts to one surface only. The parts should then be mated together under slight pressure. This causes the adhesive to spread out into a thin film and assures optimum adhesive performance. The pressure need only be applied for several seconds. The advanced performance series cures rapidly allowing for bonded parts to be handled within 20 to 60 seconds for most applications. Full cure is normally within 24 hours. In cases where CA PLUS Accelerator is used, fixturing will normally occur in less than 5 seconds with full cure in 8 hours.

Shelf Life:

All of the No Odor / No Bloom series products have a shelf life of one year when stored at 40°F. Shelf life at room temperature (72°F) is a minimum of six months. When stored in a refrigerator, allow the adhesive to gradually warm to room temperature prior to use. Avoid heat, direct sunlight and high moisture areas when storing. Avoid contaminating open containers

Handling Precautions:

All No Odor / No Bloom series products are non-toxic and so do not constitute a health hazard. Normal precautions should be observed. Use in areas where there is adequate ventilation. **KEEP AWAY FROM CHILDREN.**

Accidental skin bonding may occur. Use warm, soapy water to separate skin or use CA PLUS Debonder. Gradually work skin free. Do not use excessive force to pull bonded area apart: this will only result in the tearing of skin and/or cause irritation which is unnecessary.

Should eye contact occur flush with water and see a physician. Do not force the bonded area apart. When the corneal surface and eyelid are bonded together treat with a suitable anti-irritant ointment and allow the eye to remain closed. Bond separation will occur naturally within 48 hours with no damage.

While the information set forth herein is believed to be accurate as of the date hereof, the Company makes no warranty or guarantee, express or implied and disclaims all liability arising out of the use of this information. As of October 2, 2003.